

## YANTAI METASTAR SPECIAL PAPER CO LTD 1 EMAISHAN RD, ECONOMIC & TECHNOLOGY DEVELOPMENT ZONE, YANTAI SHANDONG 264006 CN



METASTAR: YT564 Meta-Aramid Paper

Flammability	Value	Test Method
Flame Rating		UL 94
0.025 mm, NC	VTM-0	ISO 9773
0.045 to 0.058 mm, NC	VTM-0	
0.059 to 0.080 mm, NC	VTM-0	
0.081 to 0.130 mm, NC	VTM-0	
Glow Wire Flammability Index		IEC 60695-2-12
0.045 to 0.058 mm	960 °C	
0.059 to 0.080 mm	960 °C	
0.081 to 0.130 mm	960 °C	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.045 to 0.058 mm	825 °C	
0.059 to 0.080 mm	825 °C	
0.081 to 0.130 mm	825 °C	
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
0.025 mm	PLC 4	
0.045 to 0.058 mm	PLC 4	
0.059 to 0.080 mm	PLC 4	
0.081 to 0.130 mm	PLC 4	
High Amp Arc Ignition (HAI)		UL 746
0.025 mm	PLC 4	
0.045 to 0.058 mm	PLC 4	
0.059 to 0.080 mm	PLC 4	
0.081 to 0.130 mm	PLC 4	
Comparative Tracking Index (CTI)	PLC 2	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4	UL 746
Arc Resistance	PLC 7	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
0.045 to 0.058 mm	210 °C	
0.059 to 0.080 mm	210 °C	
0.081 to 0.130 mm	210 °C	
RTI Str		UL 746
0.045 to 0.058 mm	210 °C	
0.059 to 0.080 mm	210 °C	
0.081 to 0.130 mm	210 °C	

Page 1 of 2 Form Number: E331406-102693065

Report Date: 5/21/2010 Last Revised: 2016-11-14

## Component - Plastics

File Number: E331406



## **Notice of Disclaimer**

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.